



TECHNICAL DATA SHEET
FERRO SILICON
FERALMET 74

TYPICAL ANALYSIS (OF OUR RAW MATERIAL)

Si	74 – 75%
Ca	0,25 – 0,4%
Al	0,25 – 0,35%
P	0,010 – 0,013%



APPLICATIONS

- Deoxydation agent in refractory and steel

MAIN SIZES

+250 microns – 2 - 5%
<75 microns – 75 - 80%

All these values have to be confirmed with each offer and sales confirmations.



BALL MILL
SIBOREX – WWW.SIBOREX.COM – M.JOLY@SIBOREX.COM



JET MILL

