



TECHNICAL DATA SHEET
MICROSILICA
960 ND

TYPICAL ANALYSIS (OF OUR RAW MATERIAL)

SiO₂	96,31%
C (Free Carbon)	1,23%
Fe₂O₃	0,12%
Al₂O₃	0,11%
CaO	0,42%
MgO	0,29%
K₂O	0,38%
L.O.I.	1,70%
> 45 my	0,27%
pH	7,10
B.D. (kg/m³)	340



Laboratory 19/08/2024

ND : Non-densified

All these values have to be confirmed with each offer and sales confirmations.



BALL MILL
SIBOREX — WWW.SIBOREX.COM — M.JOLY@SIBOREX.COM



JET MILL

