



TECHNICAL DATA SHEET
MICROSILICA
980 ND

TYPICAL ANALYSIS (OF OUR RAW MATERIAL)

SiO₂	98,63%
C (Free Carbon)	0,47%
Fe₂O₃	0,05%
Al₂O₃	0,22%
CaO	0,21%
MgO	0,15%
K₂O	0,16%
Na₂O	0,05%
P₂O₅	0,01%
SO₃	0,02%
Cl	0,02%
H₂O	0,17%
L.O.I.	0,21%
> 45 my	0,27%
pH	6,6
B.D. (kg/m³)	330



Laboratory 19/08/2024

ND : Non-densified

All these values have to be confirmed with each offer and sales confirmations.



BALL MILL
SIBOREX — WWW.SIBOREX.COM — M.JOLY@SIBOREX.COM



JET MILL

